

**PRODUCT DATA SHEET  
CLEAR LACQUER**

<b><u>PRODUCT NAME:</u></b>	LACQUER CLEAR
<b><u>FINISH:</u></b>	FULL GLOSS
<b><u>COLOUR:</u></b>	CLEAR
<b><u>VEHICLE TYPE:</u></b>	ALKYD NITROCELLULOSE
<b><u>PIGMENT TYPE:</u></b>	INORGANIC AND ORGANIC PHTHALOCHROMES
<b><u>SOLVENT TYPE:</u></b>	AROMATIC AND ALIPHATIC HYDROCARBONS, ESTERS, KETONES AND ALCOHOLS
<b><u>FLASH POINT MIN:</u></b>	-4°C
<b><u>SPECIFIC GRAVITY:</u></b>	0.900 – 1.090 AT 25°C MIXED
<b><u>SOLIDS CONTENT:</u></b>	35 – 40% BY WEIGHT MIXED
<b><u>THINNING RATIO:</u></b>	+ - 1 TO 1 BY VOLUME
<b><u>RECOMMENDED THINNER:</u></b>	B&R LACQUER THINNER
<b><u>VISCOSITY OF BASE AT 25°C:</u></b>	850 - 900 cpu
<b><u>DRYING TIME:</u></b>	<b><u>SURFACE:</u></b> 5 MINUTES AT 25°C
	<b><u>HARD:</u></b> 30 MINUTES AT 25°C
<b><u>APPLICATION METHOD:</u></b>	CONVENTIONAL SPRAY OR AIRLESS SPRAY.
<b><u>APPLICATION VISCOSITY:</u></b>	CONVENTIONAL GUN OR PRESSURE POT: 18 – 20" FORD CUP 4
<b><u>FINENESS OF GRIND:</u></b>	10 MICRONS
<b><u>RECOMMENDED PRIMER:</u></b>	SANDING SEALER
<b><u>RECOMMENDED DRY FILM THICKNESS:</u></b>	20 – 30 MICRONS PER COAT

**DESCRIPTION & GENERAL USE:**

A top quality nitrocellulose lacquer for use on all wooden surfaces as well as for general industrial use on steel. The product must be used in a well-ventilated area only.

**PRODUCT SAFETY DATA**

FLASH POINT	:	<5°C
HIGHLY FLAMMABLE	:	Always store in a cool place. If set alight, use only powder fire extinguishers.

**B & R PRODUCTS (PTY) LTD**

19 Beryllium Rd, Alrode Ext 7, Alberton  
Tel: 011 864-1301 /1302 /1036 /1393  
Fax: 027 11 864-1390  
P.O. Box 1633, Randburg, 2125, South Africa

Reg. No. 80/09849/07  
Email: [bandr@icon.co.za](mailto:bandr@icon.co.za)  
Web: [www.bandr.co.za](http://www.bandr.co.za)

- SKIN CONTACT : Wash immediately with lots of soap and water
- EYE CONTACT : Rinse with lots of water and seek medical attention as soon as possible.
- IF INGESTED : Do not induce vomiting. Seek medical attention immediately.

