

**PRODUCT DATA SHEET  
GENERAL PURPOSE  
ALUMINIUM**

<b><u>PRODUCT NAME:</u></b>	GENERAL PURPOSE ALUMINIUM
<b><u>FINISH:</u></b>	GLOSS
<b><u>VEHICLE TYPE:</u></b>	ALKYD
<b><u>PIGMENT TYPE:</u></b>	NON LEAFING ALUMINIUM
<b><u>SOLVENT TYPE:</u></b>	AROMATIC HYDROCARBONS
<b><u>FLASH POINT MIN:</u></b>	22°C
<b><u>SPECIFIC GRAVITY:</u></b>	1.200 – 1.250 AT 25°C
<b><u>SOLIDS CONTENT:</u></b>	60 – 65% BY WEIGHT
<b><u>RECOMMENDED DRY FILM THICKNESS:</u></b>	40um MIN
<b><u>COVERAGE AT DFT 40um:</u></b>	8m <sup>2</sup> l - 1
<b><u>VISCOSITY AT 25°C:</u></b>	65 k.u.
<b><u>DRYING TIME:</u></b>	<b><u>SURFACE:</u></b> 15 – 30 MINUTES <b><u>HARD:</u></b> 2 – 3 HOURS
<b><u>RECOMMENDED THINNER:</u></b>	ENAMEL THINNERS
<b><u>APPLICATION:</u></b>	BRUSH OR CONVENTIONAL SPRAY
<b><u>APPLICATION VISCOSITY:</u></b>	BRUSH: READY FOR USE SPRAY: 18 – 20" FC4
<b><u>FINENESS OF GRIND:</u></b>	10um

**DESCRIPTION:**

A GENERAL PURPOSE INDUSTRIAL ALUMINIUM FOR USE ON ALL STEEL SURFACES.

ALL EQUIPMENT SHOULD BE CLEANED THOROUGHLY IMMEDIATELY AFTER USE WITH THINNERS.