

**PRODUCT DATA SHEET
GENERAL PURPOSE INDUSTRIAL
PRIMER RED OXIDE**

<u>PRODUCT NAME:</u>	GENERAL PURPOSE INDUSTRIAL PRIMER RED OXIDE
<u>FINISH:</u>	MATT
<u>VEHICLE TYPE:</u>	ALKYD
<u>PIGMENT TYPE:</u>	SYNTHETIC IRON OXIDE
<u>SOLVENT TYPE:</u>	AROMATIC HYDROCARBONS
<u>FLASH POINT MIN:</u>	22°C
<u>SPECIFIC GRAVITY:</u>	1.200 – 1.250 AT 25°C
<u>SOLIDS CONTENT:</u>	60 – 65% BY WEIGHT
<u>VISCOSITY AT 25°C:</u>	650 cPu
<u>DRYING TIME:</u>	<u>SURFACE:</u> 15 – 30 MINUTES
	<u>HARD:</u> 2 – 3 HOURS
<u>APPLICATION METHOD:</u>	BRUSH OR CONVENTIONAL SPRAY
<u>APPLICATION VISCOSITY:</u>	BRUSH: READY FOR USE CONVENTIONAL SPRAY: 18 – 20 FC4
<u>RECOMMENDED THINNER:</u>	ENAMEL THINNERS
<u>FINENESS OF GRIND:</u>	10 MICRONS
<u>COVERAGE AT DFT 40 MICRONS:</u>	8 SQUARE METRES PER LITRE
<u>RECOMMENDED DRY FILM THICKNESS:</u>	40 MICRONS

DESCRIPTION & GENERAL USE:

A general purpose industrial primer for use on bare mild steel or galvanized iron for temporary protection against corrosion before finishing coats are applied. This product is not intended as a heavy duty anti-corrosive primer nor as a finishing coat on its own, but should be overcoated within six months of application.

All equipment must be cleaned immediately after use with enamel thinners.