

**PRODUCT DATA SHEET  
SUPER EGGSHELL ENAMEL**

<b><u>PRODUCT NAME:</u></b>	SUPER EGGSHELL ENAMEL
<b><u>PRODUCT BRAND:</u></b>	SUPREME
<b><u>FINISH:</u></b>	SATIN
<b><u>COLOUR:</u></b>	WHITE AND PASTEL TINTS
<b><u>VEHICLE TYPE:</u></b>	MEDIUM OIL ALKYD
<b><u>PIGMENT TYPE:</u></b>	INORGANIC
<b><u>SOLVENT TYPE:</u></b>	ALIPHATIC AND AROMATIC HYDROCARBONS
<b><u>FLASH POINT MIN:</u></b>	18°C
<b><u>SPECIFIC GRAVITY:</u></b>	1.150 – 1.175 AT 25°C
<b><u>SOLIDS CONTENT:</u></b>	60 – 70% BY WEIGHT
<b><u>VISCOSITY AT 25°C:</u></b>	800 - 850 cPu
<b><u>DRYING TIME:</u></b>	<b><u>SURFACE:</u></b> 2 HOURS
	<b><u>HARD:</u></b> 6 – 8 HOURS
<b><u>OVERCOATING TIME:</u></b>	MIN 6 HOURS AT 25 DEGREES CELSIUS
<b><u>APPLICATION METHOD:</u></b>	BRUSH, ROLLER OR CONVENTIONAL SPRAY
<b><u>APPLICATION VISCOSITY:</u></b>	BRUSH OR ROLLER: READY FOR USE CONVENTIONAL SPRAY: 18 – 20 FC4
<b><u>RECOMMENDED THINNER:</u></b>	ENAMEL THINNERS
<b><u>FINENESS OF GRIND:</u></b>	5 - 10 MICRONS
<b><u>COVERAGE AT DFT 30 MICRONS:</u></b>	6 SQUARE METRES PER LITRE (DEPENDING ON SURFACE PROFILE)
<b><u>RECOMMENDED DRY FILM THICKNESS:</u></b>	30 - 40 MICRONS

**DESCRIPTION & GENERAL USE:**

A top quality brushing, alkyd enamel for interior and exterior household use on all types of firm, clean substrates. Wood and metals should be primed with the appropriate primer and given a coat of supreme universal undercoat before applying the enamel topcoat. Cement, plaster and brickwork should first be sealed with supreme bonding liquid and allowed to dry for 6 – 8 hours.

All equipment must be cleaned immediately after use with turps or enamel thinners.