

**PRODUCT DATA SHEET
UNIVERSAL UNDERCOAT**

<u>PRODUCT NAME:</u>	UNIVERSAL UNDERCOAT
<u>PRODUCT BRAND:</u>	SUPREME
<u>FINISH:</u>	MATT
<u>COLOUR:</u>	WHITE
<u>VEHICLE TYPE:</u>	MEDIUM OIL ALKYD
<u>PIGMENT TYPE:</u>	INORGANIC
<u>SOLVENT TYPE:</u>	ALIPHATIC AND AROMATIC HYDROCARBONS
<u>FLASH POINT MIN:</u>	18°C
<u>SPECIFIC GRAVITY:</u>	1.150 – 1.170 AT 25°C
<u>SOLIDS CONTENT:</u>	50 – 60% BY WEIGHT
<u>VISCOSITY AT 25 °C:</u>	750 - 800 cPu
<u>DRYING TIME:</u>	<u>SURFACE:</u> 90 MINUTES
	<u>HARD:</u> 5 – 7 HOURS
<u>OVERCOATING TIME:</u>	MIN. 6 HOURS AT 25°C
<u>APPLICATION METHOD:</u>	BRUSH, ROLLER OR SPRAY
<u>FINENESS OF GRIND:</u>	5 – 10 MICRONS
<u>COVERAGE AT DFT 30 MICRONS:</u>	6 SQUARE METRES PER LITRE ON NON-POROUS SUBSTRATE
<u>RECOMMENDED DRY FILM THICKNESS:</u>	30 - 40 MICRONS MIN PER COAT

DESCRIPTION & GENERAL USE:

A high quality alkyd-based undercoat for use on metal, wood, plaster, cement or masonry where the intended topcoat is an alkyd-based enamel. Wood and metal must be sealed or primed with the appropriate sealer or primer before the undercoat is applied. Cement and plaster should be sealed with Supreme Bonding Liquid before applying the undercoat.

NOTE: If the undercoat is to be sprayed, it must be thinned to 18-20" Ford Cup 4 with turps or enamel thinners. Do not use lacquer thinners for this purpose.

All equipment must be cleaned after use with turps or enamel thinners.